



Technical Data Sheet

LIQUID ASPHALT

MULTI-PURPOSE LIQUIFIED ASPHALT

INTRODUCTION

AWAZEL LIQUID ASPHALT is a cold applied bituminous paint formulated with asphalt and selected petroleum solvent.

ADVANTAGES

- Ideal as damp coat
- Resists the attack of salts, acids and alkalis
- Cold applied, easy to apply, does not need thinning or heating
- Exceeds the requirements of ASTM D 2027

USES

LIQUID ASPHALT is a general purpose bituminous coating for multi-purpose applications to concrete and masonry surfaces above or below ground level.

INSTRUCTIONS FOR APPLICATION

Surface Preparation: The surfaces must be thoroughly cleaned and free of dirt, dust, debris, grease and oil. New concrete surfaces should be cured before applying LIQUID ASPHALT.

Application: After stirring, LIQUID ASPHALT can be applied with brush, roller or spray equipment. Two coats are preferable for better results. The first coat should be dry before applying the second coat.

CLEANING

LIQUID ASPHALT can be removed from equipment and tools with any suitable solvent such as gasoline or kerosene.

COVERAGE

Approximate rate for one coat: 0.35 - 0.45 kg/m². The exact rate will depend on the porosity and smoothness of the surface.

HEALTH & SAFETY

Workers should wear protective masks, gloves and goggles during application.

PRECAUTIONS

LIQUID ASPHALT contains volatile solvent and has a low flash point. Care must be taken to ensure that there is adequate ventilation in the working place. Fires and naked flames should be kept at a distance.

PACKING

LIQUID ASPHALT is packed in 140kg drums and 16kg cans. Other weights are available upon request.

STORAGE

Store in a dry and shaded area in original packing. The container should be kept covered while working in order to prevent the evaporation of the solvent.

LIQUID ASPHALT

TECHNICAL DATA

Properties	Typical Data	Test Method
Saybolt Furol Viscosity at 50°C, seconds	50 - 150	ASTM D 88
Flash Point (Tag Open Cup), °C	> 50	ASTM D 3143
Water, volume %	Nil	ASTM D 95